

RECKLI surface retarder (positive process)

Texture the concrete element using a solvent-based concrete surface retarder.

Surface retarder:

RECKLI-CR type PV (wash depth approx. x.x mm, see surface retarder application)

Aggregate size:

x-x mm (depending on the choice of surface retarder and wash depth, see surface retarder application)

Execution:

Mix the RECKLI surface retarder well, then evenly apply over the full surface of the absolutely fresh concrete using an airless spray process.

Usage: approx. 200 g/m²

The concrete should be washed once dry (1–3 days) using a pressure washer (70–150 bar). (distance at least 30 cm)

Work should be carried out in compliance with the "RECKLI surface retarder manual".