



RECKLI Surface Retarder CR Type PV (positive process)

Texture a concrete element using a solvent-based concrete surface retarder.

Surface retarder:

RECKLI CR Type PV (wash depth approx. x.x mm, see "RECKLI Surface Retarder Brochure")

Aggregate factor:

x-x mm (depending on the choice of surface retarder and wash depth, see "RECKLI Surface Retarder Brochure")

Execution:

Mix the RECKLI surface retarder well, then apply it evenly over the full surface of the absolutely fresh concrete using an airless spray process.

Usage: approx. 200 g/m²

The concrete should be washed once dry (1-3 days) using a pressure washer (70-150 bar, distance at least 30 cm).

Work should be carried out in compliance with the "RECKLI Surface Retarder Brochure".