

RECKLI[®] Construction Resin EP Rapid

modified epoxy resin

RECKLI Construction
Resin EP Rapid

Product 07126
Edition 07/24

PROPERTIES

RECKLI Construction Resin EP Rapid is a transparent, solvent-free, liquid two-component epoxy resin with a practical mixing ratio of 2 : 1 (according to weight). On exposure to direct sunlight or UV irradiation, the resin is gradually yellowing; however, without degradation of mechanical properties.

It is particularly suitable for applications at low temperatures (+5 °C – +10 °C) or with shortened curing time.

APPLICATIONS

RECKLI Construction Resin EP Rapid can be used for the manufacture of coatings, mortars or fillers with excellent adhesion to conventional substrates. For this purpose it can be mixed with various oven-dry fillers in the appropriate ratio. A particular area of application is the manufacture of decorative floorings with coloured quartz grainings, for example in offices, stores or sales and exhibition rooms.

TECHNICAL DATA

property	value	method
mixing ratio (base : hardener):	2 : 1	(according to weight)
workable temperature:	+5 °C – +30 °C	
viscosity of base component:	approx. 2000 mPa·s	ISO 2555
pot life (200-g-mixture at +21 °C):	approx. 15 – 20 min	
earliest loading (at +21 °C):	16 h	
full chemical and mechanical loading after:	10 – 14 days	
density:	1,15 g/cm ³	
hardness:	70 – 75 Shore D	DIN 53505
ball impression hardness:	65 – 70 N/mm ²	DIN 53456
heat resistance (dry heat):	+100 °C	
dimensional stability under heat:	45 °C	DIN 53462

These data are typical guide values. They are not destined for the generation of specifications.

RECKLI GmbH

Industriestraße 36
D-44628 Herne
Tel +49 2323 1706-0
Fax +49 2323 1706-50
info@reckli.de
www.reckli.de

SURFACE PREPARATION

For coatings or adhesions, the substrate must be stable, sound, dry, clean and free of oil, grease or wax.

RECKLI Construction
Resin EP Rapid

Product 07126
Edition 07/24

PROCESSING

Add the hardener (B) to the base component (A) and mix them homogenously. Transfer the mixture into a second receptacle and stir it up again. Thereby the incorporation of larger amounts of air should be avoided. Fillers should be preferably added to the mixture rather than to the base component before mixing. Once mixed, the processing of the material must be completed within the pot life (15 – 20 minutes). Mixing larger quantities decreases the processing time.

CLEANING OF EQUIPMENT

For the cleaning of the tools and the equipment use dry, absorbing cloths, if necessary RECKLI Epoxy Cleanser in addition. Immersion in solvents is not sufficient.

PACKAGING SIZES

pair of canisters: 15 kg | 7, 5 kg;

double can: 0,75 kg (the hardener is enclosed in the lid).

STORAGE

Store in a dry place at room temperature. RECKLI Construction Resin EP Rapid is storable for 6 months from delivery when kept in the closed original packaging at about 18 °C. Opened drums must be closed airtight right after use.

SPECIAL REMARKS

Storage at low temperatures may cause partial crystallisation of the base component, even if only parts of the container are exposed to cold. In this case, the material can be melted in the closed container at 40 – 50 °C. When mixed up, it is usable again.

GENERAL INFORMATION

For further information please also see:

„General advice for the processing of RECKLI two-component resins“.

SAFETY

Protect skin and eyes from material splashes. Provide sufficient ventilation in the working place. Please consult the relevant safety data sheet and attend to the indications on the label of the package regarding the Dangerous Goods Regulation. This pamphlet is intended solely as an application directive. It does not claim to be

RECKLI GmbH

Industriestraße 36
D-44628 Herne
Tel +49 2323 1706-0
Fax +49 2323 1706-50
info@reckli.de
www.reckli.de

binding and valid for all modes of application. A preliminary test under operation conditions is highly recommended.

This pamphlet replaces all previously published pamphlets concerning RECKLI Construction Resin EP Rapid, stating them as no longer being valid.

RECKLI Construction
Resin EP Rapid

Product 07126
Edition 07/24

RECKLI GmbH

Industriestraße 36
D-44628 Herne
Tel +49 2323 1706-0
Fax +49 2323 1706-50
info@reckli.de
www.reckli.de