

RECKLI[®] OS HO

RECKLI OS HO

Product 07552

Edition 01/23

Oil- and water-repellent agent

PROPERTIES

RECKLI OS HO is an aqueous hydrophobic and oleophobic concrete impregnation. It produces no lustrous effect or colour deepening.

RECKLI OS HO shows various advantages without changing the appearance and the characteristics of the treated surfaces. It is UV-resistant and water-vapour permeable. It protects the surfaces against watery as well as oily contamination, thus facilitating the subsequent cleaning with neutral cleaner. RECKLI OS HO reduces efflorescence, watercourses on facades, the growth of algae, moss or microorganisms and increases the stability against freeze-thaw cycles. Even the removal of graffiti is possible. In this case, the impregnation with RECKLI OS HO should be renewed after cleaning.

APPLICATIONS

RECKLI OS HO can be used for treating absorbent, mineral surfaces, such as concrete (washed, acid-etched, sand-blasted, bushammered, etc.), mineral plaster, clinkers, bricks, sandstone or lime sand brick.

It is particularly suitable for protecting mineral floorings, such as concrete plaster or panels, against aqueous or greasy contamination. Thus, both young and older concrete surfaces can be sustainably protected.

TECHNICAL DATA

property	value	method
appearance:	yellowish liquid	
odour:	mild	
density:	approx. 1,0 g/cm ³	ISO 2811
pH-value:	approx. 8	
viscosity:	approx. 1 mPa·s	
penetration depth:	0,05 mm	DIN EN 14630
contact angle:	151°	DIN 55660-2
resistance against liquids:	passed	
water-vapour transmission rate:	0,717 m vs. 0,705 m	DIN EN ISO 7783

These data are typical guide values. They are not destined for the generation of specifications. Certificates of mechanical values are available on request.

RECKLI GmbH

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de

SURFACE PREPARATION

Before treatment with RECKLI OS HO, the surface must be cleaned from dirt, efflorescence, algae, moss, oil or grease. For this, we recommend RECKLI Concrete Cleanser. After cleaning, the substrate must be completely dry.

RECKLI OS HO
Product 07552
Edition 01/23

PROCESSING

RECKLI OS HO should be applied in dry, calm weather conditions. The recommended substrate and ambient temperature is +5 to +25 °C. During and at least 3 hours after the application, the treated surface must be protected against rain and direct sun irradiation.

RECKLI OS HO is delivered ready for use. It is to be evenly applied with a soft brush or a suitable pneumatic atomizer. However, the formation of puddles must be avoided during the entire processing. Strongly absorbent surfaces should be coated twice fresh in fresh to ensure a sufficient protection.

CONSUMPTION

100 – 300 g/m², depending on the surface's absorbence. The preparation of an appropriate sample area is recommended.

CLEANING OF EQUIPMENT

For the cleaning of the tools and the equipment, use clear water before drying of the product.

PACKAGING SIZES

drums: 180 kg | canisters: 25 kg.

STORAGE

Store in a dry place. Protect against frost and direct sun irradiation. RECKLI OS HO is storable for 12 months after manufacture when kept in the closed original packaging at room temperature. Opened drums must be closed airtight right after use.

SPECIAL REMARKS

The tests of the physical properties mentioned above conform to the German Regelwerk für die Bewertung von Verfahren, Technologien und Materialien zur Graffiti-Entfernung und Graffiti-Prävention (ReGG III) der Gütegemeinschaft Anti-Graffiti e.V., Mitglied des RAL e.V.

RECKLI GmbH
Industriestraße 36
D-44628 Herne
Tel +49 2323 1706-0
Fax +49 2323 1706-50
info@reckli.de
www.reckli.de

SAFETY

Protect skin and eyes from material splashes. Please also consult the relevant safety data sheet. This pamphlet is intended solely as an application directive. It does not claim to be binding and valid for all modes of application. A preliminary test under operation conditions is highly recommended.

This pamphlet replaces all previously published pamphlets concerning RECKLI OS HO, stating them as no longer being valid.

RECKLI OS HO
Product 07552
Edition 01/23

RECKLI GmbH
Industriestraße 36
D-44628 Herne
Tel +49 2323 1706-0
Fax +49 2323 1706-50
info@reckli.de
www.reckli.de